

Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

SECTION 1. IDENTIFICATION

Product name Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Product code 892.177

Manufacturer or supplier's details

Würth Canada Limited Company name of supplier

Address 345 Hanlon Creek Blvd

GUELPH, ON N1C 0A1

Telephone +1 (905) 564 6225

Telefax +1 (905) 564 3671

Emergency telephone CANUTEC (24/7): +1 (613) 996-6666 or/ou *666 (cellu-

lar/cellulaire)

E-mail address prodsafe@wurth.ca

Recommended use of the chemical and restrictions on use

Recommended use **Paint**

Coatings

SECTION 2. HAZARDS IDENTIFICATION

GHS classification in accordance with the Hazardous Products Regulations

Flammable aerosols Category 1

Gases under pressure Liquefied gas

Eye irritation Category 2A

Carcinogenicity Category 2

Reproductive toxicity Category 2

Specific target organ syste-

mic toxicity - single exposure

Category 3

Specific target organ syste-

mic toxicity - repeated expo-

sure

Category 2 (Central nervous system, Liver, Kidney)

Simple Asphyxiant Category 1

GHS label elements



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Hazard pictograms









Signal Word : Danger

Hazard Statements : H222 Extremely flammable aerosol.

H280 Contains gas under pressure; may explode if heated.

H319 Causes serious eye irritation. H336 May cause drowsiness or dizziness. H351 Suspected of causing cancer.

H361d Suspected of damaging the unborn child.

H373 May cause damage to organs (Central nervous system, Liver, Kidney) through prolonged or repeated exposure. May displace oxygen and cause rapid suffocation.

Precautionary Statements

Prevention:

P201 Obtain special instructions before use.

P202 Do not handle until all safety precautions have been read and understood.

P210 Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.

P211 Do not spray on an open flame or other ignition source.

P251 Do not pierce or burn, even after use.

P260 Do not breathe spray.

P264 Wash skin thoroughly after handling.

P271 Use only outdoors or in a well-ventilated area.

P280 Wear protective gloves/ protective clothing/ eye protection/ face protection.

Response:

P304 + P340 + P312 IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a POISON

CENTER/doctor if you feel unwell.

P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P308 + P313 IF exposed or concerned: Get medical advice/

P337 + P313 If eye irritation persists: Get medical advice/ attention.

Storage:

P405 Store locked up.

P410 + P412 Protect from sunlight. Do not expose to temperatures exceeding 50 °C/ 122 °F.

Disposal:

P501 Dispose of contents/ container to an approved waste disposal plant.



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Other hazards

Repeated exposure may cause skin dryness or cracking.

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS

Substance / Mixture : Mixture

Hazardous ingredients

Chemical name	CAS-No.	Concentration (% w/w)
Acetone	67-64-1	>= 20 - < 30
Propane	74-98-6	>= 10 - < 20
Butane	106-97-8	>= 5 - < 10
Isobutyl methyl ketone	108-10-1	>= 1 - < 5
Titanium dioxide	13463-67-7	>= 1 - < 5
2-(Propyloxy)ethanol	2807-30-9	>= 1 - < 5
n-Butyl acetate	123-86-4	>= 1 - < 5
Xylene	1330-20-7	>= 1 - < 5
Pentan-2-one	107-87-9	>= 1 - < 5
Ethylethoxypropionate	763-69-9	>= 1 - < 5
Isobutyl acetate	110-19-0	>= 1 - < 5
Ethylbenzene	100-41-4	>= 0.1 - < 1
Zirconium octoate	22464-99-9	>= 0.1 - < 1

SECTION 4. FIRST AID MEASURES

In the case of accident or if you feel unwell, seek medical ad-General advice

vice immediately.

When symptoms persist or in all cases of doubt seek medical

advice.

If inhaled If inhaled, remove to fresh air.

Get medical attention.

In case of skin contact In case of contact, immediately flush skin with plenty of water.

Remove contaminated clothing and shoes.

Get medical attention. Wash clothing before reuse.

Thoroughly clean shoes before reuse.

In case of contact, immediately flush eyes with plenty of water In case of eye contact

for at least 15 minutes.

If easy to do, remove contact lens, if worn.

Get medical attention.

If swallowed If swallowed, DO NOT induce vomiting.

Get medical attention.

Rinse mouth thoroughly with water.

Most important symptoms and effects, both acute and

delayed

Causes serious eye irritation. May cause drowsiness or dizziness.

Suspected of causing cancer.



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Suspected of damaging the unborn child.

May cause damage to organs through prolonged or repeated

exposure.

Prolonged or repeated contact may dry skin and cause irrita-

Protection of first-aiders First Aid responders should pay attention to self-protection.

and use the recommended personal protective equipment

when the potential for exposure exists.

Notes to physician Treat symptomatically and supportively.

SECTION 5. FIRE-FIGHTING MEASURES

Suitable extinguishing media Water spray

> Alcohol-resistant foam Carbon dioxide (CO2)

Dry chemical

Unsuitable extinguishing

media

None known.

Specific hazards during fire

fighting

Flash back possible over considerable distance.

Vapors may form explosive mixtures with air.

Exposure to combustion products may be a hazard to health. If the temperature rises there is danger of the vessels bursting

due to the high vapor pressure.

Hazardous combustion prod- :

Carbon oxides

Metal oxides

Specific extinguishing meth-

ods

Use extinguishing measures that are appropriate to local cir-

cumstances and the surrounding environment. Use water spray to cool unopened containers.

Remove undamaged containers from fire area if it is safe to do

SO

Evacuate area.

Special protective equipment:

for fire-fighters

In the event of fire, wear self-contained breathing apparatus.

Use personal protective equipment.

SECTION 6. ACCIDENTAL RELEASE MEASURES

Personal precautions, protec- : tive equipment and emer-

gency procedures

Evacuate personnel to safe areas. Remove all sources of ignition.

Ventilate the area.

Use personal protective equipment.

Follow safe handling advice and personal protective

equipment recommendations.

Discharge into the environment must be avoided. **Environmental precautions**

Prevent further leakage or spillage if safe to do so.



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Prevent spreading over a wide area (e.g., by containment or

oil barriers).

Retain and dispose of contaminated wash water.

Local authorities should be advised if significant spillages

cannot be contained.

Methods and materials for containment and cleaning up

Non-sparking tools should be used.

Soak up with inert absorbent material.

Suppress (knock down) gases/vapors/mists with a water spray

jet.

For large spills, provide diking or other appropriate containment to keep material from spreading. If diked material can be pumped, store recovered material in appropriate container. Clean up remaining materials from spill with suitable absor-

bent.

Local or national regulations may apply to releases and disposal of this material, as well as those materials and items employed in the cleanup of releases. You will need to determine

which regulations are applicable.

Sections 13 and 15 of this SDS provide information regarding

certain local or national requirements.

SECTION 7. HANDLING AND STORAGE

Technical measures : See Engineering measures under EXPOSURE

CONTROLS/PERSONAL PROTECTION section.

Local/Total ventilation : Use with local exhaust ventilation.

Use only in an area equipped with explosion-proof exhaust ventilation if advised by assessment of the local exposure

potential

Advice on safe handling : Do not spray on an open flame or other ignition source.

Do not get on skin or clothing.

Do not breathe vapors or spray mist.

Do not swallow.

Do not get in eyes.

Handle in accordance with good industrial hygiene and safety practice, based on the results of the workplace exposure as-

sessment

Keep away from heat and sources of ignition.

Take precautionary measures against static discharges.

Take care to prevent spills, waste and minimize release to the

environment.

Conditions for safe storage : Store locked up.

Keep in a cool, well-ventilated place.

Store in accordance with the particular national regulations.

Do not pierce or burn, even after use. Keep cool. Protect from sunlight.

Materials to avoid : Do not store with the following product types:



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Date of last issue: 06/27/2017 **Revision Date:** SDS Number: 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Self-reactive substances and mixtures

Organic peroxides Oxidizing agents Flammable solids Pyrophoric liquids Pyrophoric solids

Self-heating substances and mixtures

Substances and mixtures which in contact with water emit

flammable gases

Explosives

Recommended storage tem: :

perature

49 °C

Further information on stor-

age stability

Protect from frost, heat and sunlight.

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Ingredients with workplace control parameters

Ingredients	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
Acetone	67-64-1	TWA	500 ppm 1,200 mg/m ³	CA AB OEL
		STEL	750 ppm 1,800 mg/m ³	CA AB OEL
		TWA	250 ppm	CA BC OEL
		STEL	500 ppm	CA BC OEL
		TWAEV	500 ppm 1,190 mg/m ³	CA QC OEL
		STEV	1,000 ppm 2,380 mg/m ³	CA QC OEL
		TWA	250 ppm	ACGIH
		STEL	500 ppm	ACGIH
Propane	74-98-6	TWA	1,000 ppm	CA AB OEL
		TWA	1,000 ppm	CA BC OEL
		TWAEV	1,000 ppm 1,800 mg/m ³	CA QC OEL
		TWA	1,000 ppm	CA ON OEL
Butane	106-97-8	TWA	1,000 ppm	CA AB OEL
		TWA	600 ppm	CA BC OEL
		STEL	750 ppm	CA BC OEL
		TWAEV	800 ppm 1,900 mg/m ³	CA QC OEL
		TWA	800 ppm	CA ON OEL
		STEL	1,000 ppm	ACGIH
Isobutyl methyl ketone	108-10-1	TWA	50 ppm 205 mg/m³	CA AB OEL
		STEL	75 ppm 307 mg/m³	CA AB OEL



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

 Version
 Revision Date:
 SDS Number:
 Date of last issue: 06/27/2017

 8.0
 11/29/2017
 380769-00008
 Date of first issue: 12/30/2009

	Ĭ	TWA	20 ppm	
		STEL	20 ppm	CA BC OEL
		TWAEV	75 ppm	CA BC OEL
			50 ppm 205 mg/m³	
		STEV	75 ppm 307 mg/m ³	CA QC OEL
		TWA	20 ppm	ACGIH
		STEL	75 ppm	ACGIH
Titanium dioxide	13463-67-7	TWA	10 mg/m ³	CA AB OEL
		TWAEV (to- tal dust)	10 mg/m³	CA QC OEL
		TWA (Total dust)	10 mg/m³	CA BC OEL
		TWA (respirable dust fraction)	3 mg/m³	CA BC OEL
		TWA	10 mg/m³ (Titanium dioxide)	ACGIH
2-(Propyloxy)ethanol	2807-30-9	TWA	25 ppm 110 mg/m ³	CA ON OEL
n-Butyl acetate	123-86-4	STEL	200 ppm 950 mg/m ³	CA AB OEL
		TWA	150 ppm 713 mg/m ³	CA AB OEL
		TWA	20 ppm	CA BC OEL
		TWAEV	150 ppm 713 mg/m ³	CA QC OEL
		STEV	200 ppm 950 mg/m ³	CA QC OEL
		TWA	50 ppm	ACGIH
		STEL	150 ppm	ACGIH
Xylene	1330-20-7	STEL	150 ppm 651 mg/m ³	CA AB OEL
		TWA	100 ppm 434 mg/m³	CA AB OEL
		TWAEV	100 ppm 434 mg/m³	CA QC OEL
		STEV	150 ppm 651 mg/m³	CA QC OEL
		TWA	100 ppm	CA BC OEL
		STEL	150 ppm	CA BC OEL
		TWA	100 ppm	ACGIH
		STEL	150 ppm	ACGIH
Pentan-2-one	107-87-9	STEL	250 ppm 881 mg/m ³	CA AB OEL
		TWA	200 ppm 705 mg/m ³	CA AB OEL
		TWA	150 ppm	CA BC OEL
		STEL	250 ppm	CA BC OEL
		TWAEV	150 ppm 530 mg/m³	CA QC OEL
		STEL	150 ppm	ACGIH



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

 Version
 Revision Date:
 SDS Number:
 Date of last issue: 06/27/2017

 8.0
 11/29/2017
 380769-00008
 Date of first issue: 12/30/2009

Ethylethoxypropionate	763-69-9	TWA	50 ppm 300 mg/m ³	CA ON OEL
Isobutyl acetate	110-19-0	TWA	150 ppm 713 mg/m³	CA AB OEL
		TWA	150 ppm	CA BC OEL
		TWAEV	150 ppm 713 mg/m³	CA QC OEL
		TWA	50 ppm	ACGIH
		STEL	150 ppm	ACGIH
Ethylbenzene	100-41-4	TWA	100 ppm 434 mg/m³	CA AB OEL
		STEL	125 ppm 543 mg/m³	CA AB OEL
		TWA	20 ppm	CA BC OEL
		TWAEV	100 ppm 434 mg/m³	CA QC OEL
		STEV	125 ppm 543 mg/m ³	CA QC OEL
		TWA	20 ppm	ACGIH
Zirconium octoate	22464-99-9	TWA	5 mg/m³ (Zirconium)	CA AB OEL
		STEL	10 mg/m³ (Zirconium)	CA AB OEL
		TWAEV	5 mg/m³ (Zirconium)	CA QC OEL
		STEV	10 mg/m³ (Zirconium)	CA QC OEL
		TWA	5 mg/m³ (Zirconium)	CA BC OEL
		STEL	10 mg/m³ (Zirconium)	CA BC OEL
		TWA	5 mg/m³ (Zirconium)	ACGIH
		STEL	10 mg/m³ (Zirconium)	ACGIH

Biological occupational exposure limits

Ingredients	CAS-No.	Control parameters	Biological specimen	Sam- pling time	Permissible concentration	Basis
Acetone	67-64-1	Acetone	Urine	End of shift (As soon as possible after exposure ceases)	25 mg/l	ACGIH BEI
Ethylbenzene	100-41-4	Sum of mandelic acid and phenyl gly-	Urine	End of shift (As soon as possible	0.15 g/g creatinine	ACGIH BEI



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

		oxylic acid		after exposure ceases)		
Isobutyl methyl ketone	108-10-1	methyl isobutyl ketone	Urine	End of shift (As soon as possible after exposure ceases)	1 mg/l	ACGIH BEI
Xylene	1330-20-7	Methyl- hippuric acids	Urine	End of shift (As soon as possible after exposure ceases)	1.5 g/g creatinine	ACGIH BEI

Engineering measures : Minimize workplace exposure concentrations.

Use only in an area equipped with explosion-proof exhaust ventilation if advised by assessment of the local exposure

potential

Use with local exhaust ventilation.

Personal protective equipment

Respiratory protection : Use respiratory protection unless adequate local exhaust

ventilation is provided or exposure assessment demonstrates that exposures are within recommended exposure guidelines.

Hand protection

Material : Protective gloves

Remarks : Choose gloves to protect hands against chemicals depending

on the concentration specific to place of work. For special applications, we recommend clarifying the resistance to chemicals of the aforementioned protective gloves with the glove manufacturer. Wash hands before breaks and at the end of workday. Breakthrough time is not determined for the pro-

duct. Change gloves often!

Eye protection : Wear the following personal protective equipment:

Safety goggles

Skin and body protection : Select appropriate protective clothing based on chemical

resistance data and an assessment of the local exposure

potential.

Wear the following personal protective equipment:

Flame retardant antistatic protective clothing, unless assessment demonstrates that the risk of explosive atmospheres

or flash fires is low

Skin contact must be avoided by using impervious protective



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

clothing (gloves, aprons, boots, etc).

Hygiene measures : Ensure that eye flushing systems and safety showers are

located close to the working place. When using do not eat, drink or smoke. Wash contaminated clothing before re-use.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance : Aerosol containing a liquefied gas

Color : yellow

Odor : solvent

Odor Threshold : No data available

pH : No data available

Melting point/freezing point : No data available

Initial boiling point and boiling

range

-42 °C

Flash point : -35 °C

Active ingredient

Evaporation rate : 5.6

Flammability (solid, gas) : Extremely flammable aerosol.

Upper explosion limit / Upper

flammability limit

16 %(V)

Lower explosion limit / Lower

flammability limit

1 %(V)

Vapor pressure : Not applicable

Relative vapor density : 5

Relative density : No data available

Density : 0.8 g/cm³

Solubility(ies)

Water solubility : No data available

Partition coefficient: n-

octanol/water

: Not applicable

Autoignition temperature : No data available



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Decomposition temperature : No data available

Viscosity

Viscosity, kinematic : Not applicable

Explosive properties : Not explosive

Oxidizing properties : The substance or mixture is not classified as oxidizing.

Particle size : Not applicable

SECTION 10. STABILITY AND REACTIVITY

Reactivity : Not classified as a reactivity hazard.

Chemical stability : Stable under normal conditions.

Possibility of hazardous reac-

tions

Extremely flammable aerosol.

Vapors may form explosive mixture with air.

If the temperature rises there is danger of the vessels bursting

due to the high vapor pressure.
Can react with strong oxidizing agents.

Conditions to avoid : Heat, flames and sparks.

Incompatible materials : Oxidizing agents

Hazardous decomposition

products

No hazardous decomposition products are known.

SECTION 11. TOXICOLOGICAL INFORMATION

Information on likely routes of exposure

Inhalation Skin contact Ingestion Eye contact

Acute toxicity

Not classified based on available information.

Product:

Acute oral toxicity : Acute toxicity estimate: > 5,000 mg/kg

Method: Calculation method

Acute inhalation toxicity : Acute toxicity estimate: > 40 mg/l

Exposure time: 4 h
Test atmosphere: vapor
Method: Calculation method

Acute dermal toxicity : Acute toxicity estimate: > 5,000 mg/kg

Method: Calculation method



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version 8.0

Revision Date: 11/29/2017

SDS Number: 380769-00008

Date of last issue: 06/27/2017 Date of first issue: 12/30/2009

Ingredients:

Acetone:

Acute oral toxicity : LD50 (Rat): > 5,000 mg/kg

Acute inhalation toxicity : LC50 (Rat): > 40 mg/l

Exposure time: 4 h
Test atmosphere: vapor

Acute dermal toxicity : LD50 (Rabbit): > 5,000 mg/kg

Propane:

Acute inhalation toxicity : LC50 (Rat): > 800000 ppm

Exposure time: 15 min Test atmosphere: gas

Butane:

Acute inhalation toxicity : LC50 (Rat): 658 mg/l

Exposure time: 4 h
Test atmosphere: vapor

Isobutyl methyl ketone:

Acute oral toxicity : LD50 (Rat): 2,080 mg/kg

Acute inhalation toxicity : LC50 (Rat): 11.6 mg/l

Exposure time: 4 h
Test atmosphere: vapor

Acute dermal toxicity : LD50 (Rat): > 2,000 mg/kg

Method: OECD Test Guideline 402

Assessment: The substance or mixture has no acute dermal

toxicity

Titanium dioxide:

Acute oral toxicity : LD50 (Rat): > 5,000 mg/kg

Acute inhalation toxicity : LC50 (Rat): > 6.82 mg/l

Exposure time: 4 h

Test atmosphere: dust/mist

Assessment: The substance or mixture has no acute inhala-

tion toxicity

2-(Propyloxy)ethanol:

Acute oral toxicity : LD50 (Mouse): 3,089 mg/kg

Acute dermal toxicity : LD50 (Rabbit): 1,337 mg/kg

n-Butyl acetate:

Acute oral toxicity : LD50 (Rat): > 5,000 mg/kg



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Acute inhalation toxicity : LC50 (Rat): > 21.1 mg/l

Exposure time: 4 h
Test atmosphere: vapor

Method: OECD Test Guideline 403

Acute dermal toxicity : LD50 (Rabbit): > 5,000 mg/kg

Xylene:

Acute oral toxicity : LD50 (Rat): 4,300 mg/kg

Method: Directive 67/548/EEC, Annex V, B.1.

Acute inhalation toxicity : LC50 (Rat): 27.5 mg/l

Exposure time: 4 h
Test atmosphere: vapor

Acute toxicity estimate: 11 mg/l

Exposure time: 4 h
Test atmosphere: vapor
Method: Expert judgment

Remarks: Based on harmonised classification in EU regulation

1272/2008, Annex VI

Acute dermal toxicity : Acute toxicity estimate: 1,100 mg/kg

Method: Expert judgment

Remarks: Based on harmonised classification in EU regulation

1272/2008, Annex VI

Pentan-2-one:

Acute oral toxicity : LD50 (Rat): 1,600 - 3,200 mg/kg

Acute inhalation toxicity : LC50 (Rat): > 25.5 mg/l

Exposure time: 4 h
Test atmosphere: vapor

Method: OECD Test Guideline 436

Assessment: The substance or mixture has no acute inhala-

tion toxicity

Acute dermal toxicity : LD50 (Rabbit): > 5,000 mg/kg

Ethylethoxypropionate:

Acute oral toxicity : LD50 (Rat): 4,309 mg/kg

Method: OECD Test Guideline 401

Acute dermal toxicity : LD50 (Rabbit): 4,080 mg/kg

Isobutyl acetate:

Acute oral toxicity : LD50 (Rat): 13,413 mg/kg

Acute inhalation toxicity : LC50 (Rat): > 30 mg/l

Exposure time: 6 h



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Test atmosphere: vapor

Remarks: Based on data from similar materials

Acute dermal toxicity : LD50 (Rabbit): > 17,400 mg/kg

Ethylbenzene:

Acute oral toxicity : LD50 (Rat): 3,500 mg/kg

Acute inhalation toxicity : LC50 (Rat): 17.2 mg/l

Exposure time: 4 h
Test atmosphere: vapor

Acute dermal toxicity : LD50 (Rabbit): > 5,000 mg/kg

Zirconium octoate:

Acute oral toxicity : LD50 (Rat): 2,043 mg/kg

Remarks: Based on data from similar materials

Acute inhalation toxicity : LC50 (Rat): > 4.3 mg/l

Exposure time: 4 h

Test atmosphere: dust/mist

Method: OECD Test Guideline 436

Remarks: Based on data from similar materials

Acute dermal toxicity : LD50 (Rat): > 2,000 mg/kg

Method: OECD Test Guideline 402

Assessment: The substance or mixture has no acute dermal

toxicity

Remarks: Based on data from similar materials

Skin corrosion/irritation

Not classified based on available information.

Ingredients:

Acetone:

Assessment: Repeated exposure may cause skin dryness or cracking.

Isobutyl methyl ketone:

Species: Rabbit

Method: OECD Test Guideline 404

Result: No skin irritation

Assessment: Repeated exposure may cause skin dryness or cracking.

Titanium dioxide:

Species: Rabbit

Result: No skin irritation

2-(Propyloxy)ethanol:



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Species: Rabbit

Result: No skin irritation

n-Butyl acetate:

Species: Rabbit

Result: No skin irritation

Assessment: Repeated exposure may cause skin dryness or cracking.

Xylene:

Species: Rabbit Result: Skin irritation

Pentan-2-one:

Species: Guinea pig

Method: OECD Test Guideline 404

Result: No skin irritation

Ethylethoxypropionate:

Assessment: Repeated exposure may cause skin dryness or cracking.

Isobutyl acetate:

Assessment: Repeated exposure may cause skin dryness or cracking.

Zirconium octoate:

Species: Rabbit

Method: OECD Test Guideline 404

Result: No skin irritation

Serious eye damage/eye irritation

Causes serious eye irritation.

Ingredients:

Acetone:

Species: Rabbit

Result: Irritation to eyes, reversing within 21 days

Method: OECD Test Guideline 405

Isobutyl methyl ketone:

Result: Irritation to eyes, reversing within 21 days

Remarks: Based on harmonised classification in EU regulation 1272/2008, Annex VI

Titanium dioxide:

Species: Rabbit

Result: No eye irritation



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

2-(Propyloxy)ethanol:

Species: Rabbit

Result: Irritation to eyes, reversing within 21 days

n-Butyl acetate:

Species: Rabbit

Result: No eye irritation

Method: OECD Test Guideline 405

Xylene:

Species: Rabbit

Result: Irritation to eyes, reversing within 7 days

Pentan-2-one:

Species: Rabbit

Result: Irritation to eyes, reversing within 7 days

Ethylethoxypropionate:

Species: Rabbit

Result: No eye irritation

Isobutyl acetate:

Species: Rabbit

Result: No eye irritation

Method: OECD Test Guideline 405

Remarks: Based on data from similar materials

Ethylbenzene:

Species: Rabbit

Result: No eye irritation

Zirconium octoate:

Species: Rabbit

Result: No eye irritation

Method: OECD Test Guideline 405

Respiratory or skin sensitization

Skin sensitization

Not classified based on available information.

Respiratory sensitization

Not classified based on available information.

Ingredients:

Acetone:

Test Type: Maximization Test



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Routes of exposure: Skin contact

Species: Guinea pig Result: negative

Isobutyl methyl ketone:

Test Type: Maximization Test Routes of exposure: Skin contact

Species: Guinea pig

Method: OECD Test Guideline 406

Result: negative

Titanium dioxide:

Test Type: Local lymph node assay (LLNA)

Routes of exposure: Skin contact

Species: Mouse Result: negative

2-(Propyloxy)ethanol:

Test Type: Buehler Test

Routes of exposure: Skin contact

Species: Guinea pig

Method: OECD Test Guideline 406

Result: negative

n-Butyl acetate:

Test Type: Maximization Test Routes of exposure: Skin contact

Species: Guinea pig Result: negative

Xylene:

Test Type: Local lymph node assay (LLNA)

Routes of exposure: Skin contact

Species: Mouse

Method: OECD Test Guideline 429

Result: negative

Ethylethoxypropionate:

Test Type: Freund's complete adjuvant test

Routes of exposure: Skin contact

Species: Guinea pig Result: negative

Isobutyl acetate:

Test Type: Maximization Test Routes of exposure: Skin contact

Species: Guinea pig

Method: OECD Test Guideline 406



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Result: negative

Ethylbenzene:

Test Type: Human repeat insult patch test (HRIPT)

Routes of exposure: Skin contact

Result: negative

Zirconium octoate:

Test Type: Maximization Test Routes of exposure: Skin contact

Species: Guinea pig Result: negative

Remarks: Based on data from similar materials

Germ cell mutagenicity

Not classified based on available information.

Ingredients:

Acetone:

Genotoxicity in vitro : Test Type: In vitro mammalian cell gene mutation test

Method: OECD Test Guideline 476

Result: negative

Genotoxicity in vivo : Test Type: In vivo micronucleus test

Species: Hamster

Application Route: Intraperitoneal injection

Result: negative

Propane:

Genotoxicity in vitro : Test Type: Bacterial reverse mutation assay (AMES)

Result: negative

Genotoxicity in vivo : Test Type: Mammalian erythrocyte micronucleus test (in vivo

cytogenetic assay)

Species: Rat

Application Route: inhalation (gas) Method: OECD Test Guideline 474

Result: negative

Butane:

Genotoxicity in vitro : Test Type: Bacterial reverse mutation assay (AMES)

Result: negative

Genotoxicity in vivo : Test Type: Mammalian erythrocyte micronucleus test (in vivo

cytogenetic assay)

Species: Rat

Application Route: inhalation (gas) Method: OECD Test Guideline 474

Result: negative



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Remarks: Based on data from similar materials

Isobutyl methyl ketone:

Genotoxicity in vitro : Test Type: Chromosome aberration test in vitro

Result: negative

Test Type: Bacterial reverse mutation assay (AMES)

Result: negative

Genotoxicity in vivo : Test Type: Mammalian erythrocyte micronucleus test (in vivo

cytogenetic assay) Species: Mouse

Application Route: Intraperitoneal injection

Result: negative

Titanium dioxide:

Genotoxicity in vitro : Test Type: Bacterial reverse mutation assay (AMES)

Result: negative

Genotoxicity in vivo : Test Type: In vivo micronucleus test

Species: Mouse Result: negative

2-(Propyloxy)ethanol:

Genotoxicity in vitro : Test Type: In vitro mammalian cell gene mutation test

Method: OECD Test Guideline 476

Result: negative

Test Type: Bacterial reverse mutation assay (AMES)

Method: OECD Test Guideline 471

Result: negative

Test Type: Chromosome aberration test in vitro

Method: OECD Test Guideline 473

Result: negative

n-Butyl acetate:

Genotoxicity in vitro : Test Type: Bacterial reverse mutation assay (AMES)

Result: negative

Xylene:

Genotoxicity in vitro : Test Type: Chromosome aberration test in vitro

Result: negative

Test Type: In vitro sister chromatid exchange assay in mam-

malian cells Result: negative

Genotoxicity in vivo : Test Type: Rodent dominant lethal test (germ cell) (in vivo)

Species: Mouse



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version 8.0 Revision Date: 11/29/2017

SDS Number: 380769-00008

Date of last issue: 06/27/2017 Date of first issue: 12/30/2009

Application Route: Skin contact

Result: negative

Pentan-2-one:

Genotoxicity in vitro : Test Type: Chromosome aberration test in vitro

Method: OECD Test Guideline 473

Result: negative

Ethylethoxypropionate:

Genotoxicity in vitro : Test Type: In vitro mammalian cell gene mutation test

Method: OECD Test Guideline 476

Result: negative

Isobutyl acetate:

Genotoxicity in vitro : Test Type: Chromosome aberration test in vitro

Method: OECD Test Guideline 473

Result: negative

Test Type: Bacterial reverse mutation assay (AMES)

Method: OECD Test Guideline 471

Result: negative

Genotoxicity in vivo : Test Type: Mammalian erythrocyte micronucleus test (in vivo

cytogenetic assay) Species: Mouse

Application Route: Ingestion Method: OECD Test Guideline 474

Result: negative

Remarks: Based on data from similar materials

Ethylbenzene:

Genotoxicity in vitro : Test Type: Chromosome aberration test in vitro

Result: negative

Test Type: In vitro mammalian cell gene mutation test

Method: OECD Test Guideline 476

Result: negative

Genotoxicity in vivo : Test Type: Unscheduled DNA synthesis (UDS) test with

mammalian liver cells in vivo

Species: Mouse

Application Route: Inhalation Method: OECD Test Guideline 486

Result: negative

Zirconium octoate:

Genotoxicity in vitro : Test Type: Chromosome aberration test in vitro

Method: OECD Test Guideline 473

Result: negative

Remarks: Based on data from similar materials



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Genotoxicity in vivo : Test Type: Mammalian erythrocyte micronucleus test (in vivo

cytogenetic assay) Species: Mouse

Application Route: Ingestion Method: OECD Test Guideline 474

Result: negative

Remarks: Based on data from similar materials

Carcinogenicity

Suspected of causing cancer.

Ingredients:

Acetone:

Species: Mouse

Application Route: Skin contact Exposure time: 1 Years

Result: negative

Isobutyl methyl ketone:

Species: Rat

Application Route: inhalation (vapor)

Exposure time: 2 Years

Method: OECD Test Guideline 451

Result: positive

Remarks: The mechanism or mode of action may not be relevant in humans.

Species: Mouse

Application Route: inhalation (vapor)

Exposure time: 2 Years

Method: OECD Test Guideline 451

Result: positive

Remarks: The mechanism or mode of action may not be relevant in humans.

Carcinogenicity - Assess-

ment

Weight of evidence does not support classification as a car-

cinogen

Titanium dioxide:

Species: Rat

Application Route: inhalation (dust/mist/fume)

Exposure time: 2 Years

Method: OECD Test Guideline 453

Result: positive

Remarks: The mechanism or mode of action may not be relevant in humans.

Carcinogenicity - Assess-

Limited evidence of carcinogenicity in inhalation studies with

animals.

Xylene: Species: Rat

ment



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Application Route: Ingestion Exposure time: 103 weeks

Result: negative

Ethylbenzene:

Species: Rat

. Application Route: Inhalation Exposure time: 104 weeks

Result: positive

Remarks: The mechanism or mode of action may not be relevant in humans.

Carcinogenicity - Assess-

: Limited evidence of carcinogenicity in animal studies

ment

Reproductive toxicity

Suspected of damaging the unborn child.

Ingredients:

Acetone:

Effects on fertility : Test Type: One-generation reproduction toxicity study

Species: Rat

Application Route: Ingestion

Result: negative

Effects on fetal development: Test Type: Embryo-fetal development

Species: Mouse Result: negative

Propane:

Effects on fertility : Test Type: Combined repeated dose toxicity study with the

reproduction/developmental toxicity screening test

Species: Rat

Application Route: inhalation (gas) Method: OECD Test Guideline 422

Result: negative

Effects on fetal development : Test Type: Combined repeated dose toxicity study with the

reproduction/developmental toxicity screening test

Species: Rat

Application Route: inhalation (gas) Method: OECD Test Guideline 422

Result: negative

Butane:

Effects on fertility : Test Type: Combined repeated dose toxicity study with the

reproduction/developmental toxicity screening test

Species: Rat

Application Route: inhalation (gas) Method: OECD Test Guideline 422

Result: negative



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Effects on fetal development : Test Type: Combined repeated dose toxicity study with the

reproduction/developmental toxicity screening test

Application Route: inhalation (gas) Method: OECD Test Guideline 422

Result: negative

Isobutyl methyl ketone:

Effects on fertility : Test Type: Two-generation reproduction toxicity study

Species: Rat

Application Route: inhalation (vapor) Method: OECD Test Guideline 416

Result: negative

Effects on fetal development: Test Type: Embryo-fetal development

Species: Mouse

Application Route: inhalation (vapor)

Result: negative

2-(Propyloxy)ethanol:

Effects on fetal development : Test Type: Embryo-fetal development

Species: Rabbit

Application Route: inhalation (vapor)

Result: negative

n-Butyl acetate:

Effects on fertility : Test Type: Two-generation reproduction toxicity study

Species: Rat

Application Route: inhalation (vapor) Method: OECD Test Guideline 416

Result: negative

Effects on fetal development : Test Type: Embryo-fetal development

Species: Rat

Application Route: inhalation (vapor)

Result: negative

Xylene:

Effects on fertility : Test Type: One-generation reproduction toxicity study

Species: Rat

Application Route: inhalation (vapor)

Result: negative

Effects on fetal development : Test Type: Embryo-fetal development

Species: Rat

Application Route: inhalation (vapor)

Result: negative

Pentan-2-one:

Effects on fertility : Test Type: Reproduction/Developmental toxicity screening



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

test

Species: Rat

Application Route: inhalation (vapor) Method: OECD Test Guideline 421

Result: negative

Ethylethoxypropionate:

Effects on fetal development : Test Type: Embryo-fetal development

Species: Rat

Application Route: inhalation (vapor)

Result: negative

Isobutyl acetate:

Effects on fertility : Test Type: Two-generation reproduction toxicity study

Species: Rat

Application Route: inhalation (vapor)

Method: OPPTS 870.3800

Result: negative

Remarks: Based on data from similar materials

Effects on fetal development : Test Type: Embryo-fetal development

Species: Rat

Application Route: Inhalation

Result: negative

Remarks: Based on data from similar materials

Ethylbenzene:

Effects on fertility : Test Type: Two-generation reproduction toxicity study

Species: Rat

Application Route: inhalation (vapor) Method: OECD Test Guideline 415

Result: negative

Effects on fetal development : Test Type: Embryo-fetal development

Species: Rat

Application Route: Inhalation Method: OECD Test Guideline 414

Result: negative

Zirconium octoate:

Effects on fertility : Test Type: Fertility/early embryonic development

Species: Rat

Application Route: Ingestion

Result: negative

Remarks: Based on data from similar materials

Effects on fetal development : Test Type: Embryo-fetal development

Species: Rat

Application Route: Ingestion

Result: positive

Remarks: Based on data from similar materials



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Reproductive toxicity - Assessment

Some evidence of adverse effects on development, based on

animal experiments.

STOT-single exposure

May cause drowsiness or dizziness.

Ingredients:

Acetone:

Assessment: May cause drowsiness or dizziness.

Propane:

Assessment: May cause drowsiness or dizziness.

Butane:

Assessment: May cause drowsiness or dizziness.

Isobutyl methyl ketone:

Assessment: May cause respiratory irritation.

n-Butyl acetate:

Assessment: May cause drowsiness or dizziness.

Xylene:

Assessment: May cause respiratory irritation.

Isobutyl acetate:

Assessment: May cause drowsiness or dizziness.

STOT-repeated exposure

May cause damage to organs (Central nervous system, Liver, Kidney) through prolonged or repeated exposure.

Ingredients:

Xylene:

Routes of exposure: inhalation (vapor)

Target Organs: Central nervous system, Liver, Kidney

Assessment: Shown to produce significant health effects in animals at concentrations of >0.2 to 1 mg/l/6h/d.

Ethylbenzene:

Routes of exposure: inhalation (vapor)

Target Organs: Auditory system

Assessment: Shown to produce significant health effects in animals at concentrations of >0.2 to

1 mg/l/6h/d.



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Repeated dose toxicity

Ingredients:

Acetone:

Species: Rat

LOAEL: 1,700 mg/kg Application Route: Ingestion Exposure time: 90 Days

Propane:

Species: Rat NOAEL: 7.214 mg/l

Application Route: inhalation (gas)

Exposure time: 6 Weeks

Method: OECD Test Guideline 422

Butane:

Species: Rat NOAEL: 9000 ppm

Application Route: inhalation (gas)

Exposure time: 6 Weeks

Method: OECD Test Guideline 422

Isobutyl methyl ketone:

Species: Rat

NOAEL: 1,840 mg/m³

Application Route: inhalation (vapor)

Exposure time: 13 Weeks

Titanium dioxide:

Species: Rat

NOAEL: 24,000 mg/kg Application Route: Ingestion Exposure time: 28 Days

Species: Rat NOAEL: 10 mg/m³

Application Route: inhalation (dust/mist/fume)

Exposure time: 2 y

2-(Propyloxy)ethanol:

Species: Rat LOAEL: 195 mg/kg

Application Route: Ingestion Exposure time: 6 Weeks

n-Butyl acetate:

Species: Rat



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

NOAEL: 2.4 mg/l

Application Route: inhalation (vapor)

Exposure time: 90 Days

Xylene:

Species: Rat NOAEL: 4.35 mg/l

Application Route: inhalation (vapor)

Exposure time: 90 Days

Ethylethoxypropionate:

Species: Rat

NOAEL: 1,000 mg/kg Application Route: Ingestion Exposure time: 29 Days

Method: OECD Test Guideline 407

Isobutyl acetate:

Species: Rat

NOAEL: 316 mg/kg

Application Route: Ingestion Exposure time: 92 Days

Remarks: Based on data from similar materials

Ethylbenzene:

Species: Rat, female LOAEL: 75 ppm

Application Route: inhalation (vapor)

Exposure time: 104 Weeks

Zirconium octoate:

Species: Rat

NOAEL: 300 mg/kg

Application Route: Ingestion Exposure time: 91 - 93 Days

Remarks: Based on data from similar materials

Aspiration toxicity

Not classified based on available information.

Ingredients:

Xylene:

The substance or mixture is known to cause human aspiration toxicity hazards or has to be regarded as if it causes a human aspiration toxicity hazard.

Ethylbenzene:

The substance or mixture is known to cause human aspiration toxicity hazards or has to be regarded as if it causes a human aspiration toxicity hazard.



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

II

SECTION 12. ECOLOGICAL INFORMATION

Ecotoxicity

Ingredients:

Acetone:

Toxicity to fish : LC50 (Pimephales promelas (fathead minnow)): 6,210 - 8,120

mg/l

Exposure time: 96 h

Method: OECD Test Guideline 203

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia pulex (Water flea)): 8,800 mg/l

Exposure time: 48 h

Toxicity to daphnia and other : aquatic invertebrates (Chron-

ic toxicity)

NOEC (Daphnia magna (Water flea)): 1,106 - 2,212 mg/l

Exposure time: 28 d

Isobutyl methyl ketone:

Toxicity to fish : LC50 (Danio rerio (zebra fish)): > 179 mg/l

Exposure time: 96 h

Method: OECD Test Guideline 203

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia magna (Water flea)): > 200 mg/l

Exposure time: 48 h

Method: OECD Test Guideline 202

Toxicity to daphnia and other : aquatic invertebrates (Chron-

ic toxicity)

NOEC (Daphnia magna (Water flea)): 30 mg/l

Exposure time: 21 d

Toxicity to microorganisms : EC10 (Pseudomonas putida): 275 mg/l

Exposure time: 16 h

Titanium dioxide:

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): > 100 mg/l

Exposure time: 96 h

Method: OECD Test Guideline 203

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia magna (Water flea)): > 100 mg/l

Exposure time: 48 h

Toxicity to algae : EC50 (Skeletonema costatum (marine diatom)): > 10,000 mg/l

Exposure time: 72 h

Toxicity to microorganisms : EC50: > 1,000 mg/l

Exposure time: 3 h

Method: OECD Test Guideline 209



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

2-(Propyloxy)ethanol:

Toxicity to fish LC50 (Pimephales promelas (fathead minnow)): > 5,000 mg/l

Exposure time: 96 h

aquatic invertebrates

Toxicity to daphnia and other : EC50 (Daphnia magna (Water flea)): > 5,000 mg/l

Exposure time: 48 h

NOEC (Pseudokirchneriella subcapitata (green algae)): >= Toxicity to algae

100 ma/l

Exposure time: 72 h

Method: OECD Test Guideline 201

ErC50 (Pseudokirchneriella subcapitata (green algae)): > 100

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Toxicity to microorganisms : IC50: > 1,000 mg/l

Exposure time: 16 h

n-Butyl acetate:

Toxicity to fish LC50 (Pimephales promelas (fathead minnow)): 18 mg/l

Exposure time: 96 h

Toxicity to daphnia and other:

aquatic invertebrates

EC50 (Daphnia sp. (Water flea)): 44 mg/l

Exposure time: 48 h

ErC50 (Pseudokirchneriella subcapitata (green algae)): 397 Toxicity to algae

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Remarks: Based on data from similar materials

NOEC (Pseudokirchneriella subcapitata (green algae)): 196

ma/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Remarks: Based on data from similar materials

Toxicity to daphnia and other : aquatic invertebrates (Chron-

ic toxicity)

NOEC (Daphnia magna (Water flea)): 23.2 mg/l

Exposure time: 21 d

Method: OECD Test Guideline 211

Remarks: Based on data from similar materials

Toxicity to microorganisms IC50 (Tetrahymena pyriformis): 356 mg/l

Exposure time: 40 h

Xylene:

LC50 (Oncorhynchus mykiss (rainbow trout)): 2.6 mg/l Toxicity to fish

Exposure time: 96 h

Method: OECD Test Guideline 203

Remarks: Based on data from similar materials



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Toxicity to daphnia and other :

aquatic invertebrates

IC50 (Daphnia magna (Water flea)): 1 mg/l

Exposure time: 24 h

Method: OECD Test Guideline 202

Remarks: Based on data from similar materials

Toxicity to algae : EC10 (Pseudokirchneriella subcapitata (green algae)): 1.9

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Remarks: Based on data from similar materials

ErC50 (Pseudokirchneriella subcapitata (green algae)): 4.36

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Remarks: Based on data from similar materials

Toxicity to fish (Chronic tox-

icity)

NOEC (Oncorhynchus mykiss (rainbow trout)): > 1.3 mg/l

Exposure time: 56 d

Toxicity to daphnia and other :

aquatic invertebrates (Chron-

ic toxicity)

EC10 (Daphnia magna (Water flea)): 1.91 mg/l

Exposure time: 21 d

Method: OECD Test Guideline 211

Remarks: Based on data from similar materials

Toxicity to microorganisms : EC50: > 157 mg/l

Exposure time: 3 h

Method: OECD Test Guideline 209

Remarks: Based on data from similar materials

Pentan-2-one:

Toxicity to fish : LC50 (Pimephales promelas (fathead minnow)): 1,240 mg/l

Exposure time: 96 h

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia magna (Water flea)): > 110 mg/l

Exposure time: 48 h

Method: OECD Test Guideline 202

Toxicity to algae : EC50 (Pseudokirchneriella subcapitata (green algae)): > 150

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

NOEC (Pseudokirchneriella subcapitata (green algae)): 73.77

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Ethylethoxypropionate:

Toxicity to fish : LC50 (Pimephales promelas (fathead minnow)): 55.3 mg/l

Exposure time: 96 h



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Method: OECD Test Guideline 203

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia magna (Water flea)): > 479.7 mg/l

Exposure time: 48 h

Method: OECD Test Guideline 202

Toxicity to algae : EC50 (Pseudokirchneriella subcapitata (green algae)): >

114.86 mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

NOEC (Pseudokirchneriella subcapitata (green algae)):

114.86 mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Toxicity to microorganisms : NOEC: 500 mg/l

Exposure time: 16 h

Isobutyl acetate:

Toxicity to fish : LC50 (Oryzias latipes (Japanese medaka)): 17 mg/l

Exposure time: 96 h

Method: OECD Test Guideline 203

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia magna (Water flea)): 25 mg/l

Exposure time: 48 h

Method: OECD Test Guideline 202

Toxicity to algae : ErC50 (Pseudokirchneriella subcapitata (green algae)): 370

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

NOEC (Pseudokirchneriella subcapitata (green algae)): 95

mg/l

Exposure time: 72 h

Method: OECD Test Guideline 201

Toxicity to daphnia and other : aquatic invertebrates (Chron-

ic toxicity)

NOEC (Daphnia magna (Water flea)): 23 mg/l

Exposure time: 21 d

Method: OECD Test Guideline 211

Toxicity to microorganisms : EC10 (Pseudomonas putida): 200 mg/l

Exposure time: 16 h

Ethylbenzene:

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 4.2 mg/l

Exposure time: 96 h

Method: OECD Test Guideline 203

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia magna (Water flea)): 1.8 - 2.4 mg/l

Exposure time: 48 h



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Toxicity to algae : EC50 (Pseudokirchneriella subcapitata (green algae)): 5.4

mg/l

Exposure time: 72 h

Toxicity to daphnia and other :

aquatic invertebrates (Chron-

ic toxicity)

NOEC (Ceriodaphnia dubia (water flea)): 0.96 mg/l

Exposure time: 7 d

Toxicity to microorganisms : EC50 (Nitrosomonas sp.): 96 mg/l

Exposure time: 24 h

Method: OECD Test Guideline 209

Zirconium octoate:

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 180 mg/l

Exposure time: 96 h

Remarks: Based on data from similar materials

Toxicity to daphnia and other :

aquatic invertebrates

EC50 (Daphnia magna (Water flea)): > 0.17 mg/l

Exposure time: 48 h

Method: OECD Test Guideline 202

Remarks: No toxicity at the limit of solubility.

Toxicity to algae : EC50 (Desmodesmus subspicatus (green algae)): 49.3 mg/l

Exposure time: 96 h

Remarks: Based on data from similar materials

EC10 (Desmodesmus subspicatus (green algae)): 32 mg/l

Exposure time: 96 h

Remarks: Based on data from similar materials

Toxicity to daphnia and other :

aquatic invertebrates (Chron-

ic toxicity)

NOEC (Daphnia magna (Water flea)): 25 mg/l

Exposure time: 21 d

Method: OECD Test Guideline 211

Remarks: Based on data from similar materials

Toxicity to microorganisms : EC50 (Pseudomonas putida): 112.1 mg/l

Exposure time: 17 h Method: DIN 38 412 Part 8

Remarks: Based on data from similar materials

Persistence and degradability

Ingredients:

Acetone:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 91 % Exposure time: 28 d

Propane:

Biodegradability : Result: Readily biodegradable.



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Biodegradation: 100 % Exposure time: 385.5 h

Remarks: Based on data from similar materials

Butane:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 100 % Exposure time: 385.5 h

Remarks: Based on data from similar materials

Isobutyl methyl ketone:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 83 % Exposure time: 28 d

Method: OECD Test Guideline 301F

2-(Propyloxy)ethanol:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 100 % Exposure time: 20 d

n-Butyl acetate:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 83 % Exposure time: 28 d

Method: OECD Test Guideline 301D

Xylene:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 87.8 % Exposure time: 28 d

Method: OECD Test Guideline 301F

Remarks: Based on data from similar materials

Pentan-2-one:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 70 % Exposure time: 28 d

Method: OECD Test Guideline 301D

Ethylethoxypropionate:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 100 % Exposure time: 18 d

Method: OECD Test Guideline 301B

Isobutyl acetate:

Biodegradability : Result: Readily biodegradable.



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version 8.0

Revision Date: 11/29/2017

SDS Number: 380769-00008

Date of last issue: 06/27/2017 Date of first issue: 12/30/2009

Biodegradation: 81 % Exposure time: 20 d

Ethylbenzene:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 70 - 80 % Exposure time: 28 d

Zirconium octoate:

Biodegradability : Result: Readily biodegradable.

Biodegradation: 99 % Exposure time: 28 d

Method: OECD Test Guideline 301E

Remarks: Based on data from similar materials

Bioaccumulative potential

Ingredients:

Acetone:

Partition coefficient: n-

octanol/water

: log Pow: -0.24

Butane:

Partition coefficient: n-

octanol/water

log Pow: 2.31

Isobutyl methyl ketone:

Partition coefficient: n-

octanol/water

: log Pow: 1.9

2-(Propyloxy)ethanol:

Partition coefficient: n-

octanol/water

log Pow: 0.673

n-Butyl acetate:

Partition coefficient: n-

octanol/water

: log Pow: 2.3

Xylene:

Bioaccumulation : Species: Oncorhynchus mykiss (rainbow trout)

Bioconcentration factor (BCF): 5.4 - 25.9

Partition coefficient: n-

octanol/water

: log Pow: 3.12 - 3.2

Pentan-2-one:



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Partition coefficient: n-

octanol/water

: log Pow: 0.857

Ethylethoxypropionate:

Partition coefficient: n-

octanol/water

log Pow: 1.47

Isobutyl acetate:

Partition coefficient: n-

octanol/water

log Pow: 2.3

Ethylbenzene:

Bioaccumulation : Species: Fish

Bioconcentration factor (BCF): < 100

Remarks: Based on data from similar materials

Partition coefficient: n-

octanol/water

log Pow: 3.6

Mobility in soil

No data available

Other adverse effects

No data available

SECTION 13. DISPOSAL CONSIDERATIONS

Disposal methods

Waste from residues : Dispose of in accordance with local regulations.

Contaminated packaging : Empty containers should be taken to an approved waste

handling site for recycling or disposal.

Empty containers retain residue and can be dangerous. Do not pressurize, cut, weld, braze, solder, drill, grind, or expose such containers to heat, flame, sparks, or other sources of ignition. They may explode and cause injury and/or death. If not otherwise specified: Dispose of as unused product. Please ensure aerosol cans are sprayed completely empty

(including propellant)

SECTION 14. TRANSPORT INFORMATION

International Regulations

UNRTDG

UN number : UN 1950 Proper shipping name : AEROSOLS

Class : 2.

Packing group : Not assigned by regulation



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Labels : 2.1

IATA-DGR

UN/ID No. : UN 1950

Proper shipping name : Aerosols, flammable

Class : 2.1

Packing group : Not assigned by regulation

Labels : Flammable Gas

Packing instruction (cargo : 203

aircraft)

Packing instruction (passen- : 203

ger aircraft)

IMDG-Code

UN number : UN 1950
Proper shipping name : AEROSOLS

Class : 2.1

Packing group : Not assigned by regulation

Labels : 2.1
EmS Code : F-D, S-U
Marine pollutant : no

Transport in bulk according to Annex II of MARPOL 73/78 and the IBC Code

Not applicable for product as supplied.

Domestic regulation

TDG

UN number : UN 1950
Proper shipping name : AEROSOLS

Class : 2.1

Packing group : Not assigned by regulation

Labels : 2.1
ERG Code : 126
Marine pollutant : no

SECTION 15. REGULATORY INFORMATION

Volatile organic compounds

(VOC) content

VOC content: 72.36 % / 574.49 g/l

The ingredients of this product are reported in the following inventories:

DSL : All chemical substances in this product comply with the CEPA

1999 and NSNR and are on or exempt from listing on the

Canadian Domestic Substances List (DSL).

SECTION 16. OTHER INFORMATION

Full text of other abbreviations

ACGIH : USA. ACGIH Threshold Limit Values (TLV)

CA QC OEL / TWAEV

CA QC OEL / STEV



Industrial Enamel Paint, Gloss, Safety Yellow, 425 q

SDS Number: Date of last issue: 06/27/2017 Version Revision Date: 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009 **ACGIH BEI** ACGIH - Biological Exposure Indices (BEI) Canada. Alberta, Occupational Health and Safety Code (table CA AB OEL 2: OEL) CA BC OEL Canada. British Columbia OEL Ontario Table of Occupational Exposure Limits made under CA ON OEL the Occupational Health and Safety Act. CA QC OEL Québec. Regulation respecting occupational health and safety, Schedule 1, Part 1: Permissible exposure values for airborne contaminants ACGIH / TWA 8-hour, time-weighted average ACGIH / STEL Short-term exposure limit CA AB OEL / TWA 8-hour Occupational exposure limit 15-minute occupational exposure limit CA AB OEL / STEL CA BC OEL / TWA 8-hour time weighted average CA BC OEL / STEL short-term exposure limit CA ON OEL / TWA Time-Weighted Average Limit (TWA)

Time-weighted average exposure value

Short-term exposure value

AICS - Australian Inventory of Chemical Substances; ANTT - National Agency for Transport by Land of Brazil; ASTM - American Society for the Testing of Materials; bw - Body weight; CMR -Carcinogen, Mutagen or Reproductive Toxicant; CPR - Controlled Products Regulations; DIN -Standard of the German Institute for Standardisation; DSL - Domestic Substances List (Canada); ECx - Concentration associated with x% response; ELx - Loading rate associated with x% response; EmS - Emergency Schedule; ENCS - Existing and New Chemical Substances (Japan); ErCx - Concentration associated with x% growth rate response; ERG - Emergency Response Guide; GHS - Globally Harmonized System; GLP - Good Laboratory Practice; IARC - International Agency for Research on Cancer; IATA - International Air Transport Association; IBC - International Code for the Construction and Equipment of Ships carrying Dangerous Chemicals in Bulk; IC50 - Half maximal inhibitory concentration; ICAO - International Civil Aviation Organization; IECSC - Inventory of Existing Chemical Substances in China; IMDG - International Maritime Dangerous Goods; IMO - International Maritime Organization; ISHL - Industrial Safety and Health Law (Japan); ISO - International Organisation for Standardization; KECI - Korea Existing Chemicals Inventory; LC50 - Lethal Concentration to 50 % of a test population; LD50 - Lethal Dose to 50% of a test population (Median Lethal Dose); MARPOL - International Convention for the Prevention of Pollution from Ships; n.o.s. - Not Otherwise Specified; Nch - Chilean Norm; NO(A)EC -No Observed (Adverse) Effect Concentration: NO(A)EL - No Observed (Adverse) Effect Level: NOELR - No Observable Effect Loading Rate; NOM - Official Mexican Norm; NTP - National Toxicology Program; NZIoC - New Zealand Inventory of Chemicals; OECD - Organization for Economic Co-operation and Development; OPPTS - Office of Chemical Safety and Pollution Prevention; PBT - Persistent, Bioaccumulative and Toxic substance; PICCS - Philippines Inventory of Chemicals and Chemical Substances; (Q)SAR - (Quantitative) Structure Activity Relationship; REACH - Regulation (EC) No 1907/2006 of the European Parliament and of the Council concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals; SADT - Self-Accelerating Decomposition Temperature; SDS - Safety Data Sheet; TCSI - Taiwan Chemical Substance Inventory; TDG - Transportation of Dangerous Goods; TSCA - Toxic Substances Control Act (United States): UN - United Nations: UNRTDG - United Nations Recommendations on the Transport of Dangerous Goods; vPvB - Very Persistent and Very Bioaccumulative; WHMIS -Workplace Hazardous Materials Information System

Sources of key data used to compile the Material Safety Data Sheet

Internal technical data, data from raw material SDSs, OECD eChem Portal search results and European Chemicals Agen-

cy, http://echa.europa.eu/



Industrial Enamel Paint, Gloss, Safety Yellow, 425 g

Version Revision Date: SDS Number: Date of last issue: 06/27/2017 8.0 11/29/2017 380769-00008 Date of first issue: 12/30/2009

Revision Date : 11/29/2017

Items where changes have been made to the previous version are highlighted in the body of this document by two vertical lines.

The information provided in this Safety Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication. The information is designed only as a guidance for safe handling, use, processing, storage, transportation, disposal and release and shall not be considered a warranty or quality specification of any type. The information provided relates only to the specific material identified at the top of this SDS and may not be valid when the SDS material is used in combination with any other materials or in any process, unless specified in the text. Material users should review the information and recommendations in the specific context of their intended manner of handling, use, processing and storage, including an assessment of the appropriateness of the SDS material in the user's end product, if applicable.

CA / Z8